

FYBATEX PANELS

General Technical Specification

General description:

Fybatex panel - **GRP** solid coloured panel, designed for use in a general cladding, lining applications. Manufactured by combining hundreds of thousands of glass strands with pigmented thermoset UV resins.

FINISHING SURFACE

Standard surfaces included:

Surfaces available for special order:

1. Woodgrain / any from standard range

- 1. Smooth / Crinkle
- 2. Smooth / Smooth
- 3. Smooth / Leatherette
- 4. Crinkle / Crinkle
- 5. Leatherette / Leatherette
- 6. Smooth / Resotex

WEIGHT OF A PANEL:

THICKNESS	WEIGHT
[mm]	[kg/m2]
3mm	4.00
4mm	5.10
5mm	6.80
6mm	8.10

FIRE RESISTANCE

Products can be manufactured to either:

- 1. General purpose (GP) grade (all products)
- 2. BS 476 Part 7 Class 1 (all products)
- 3. BS 476 Part 6 Class 'O' (all products)

4. BS 476 Part 7 Class 2 (all products)

THERMAL CO-EFFICIENT OF EXPANSION

30 x 10^(-6) /Deg C

FACT: Compared with many other plastics **GRP** has minimal expansion and contraction characteristics and will not bow and warp in extremes of temperature.

COLOUR RANGE

Panels can be manufactured to the following: B.S. 4800 Colour Range B.S. 5252 Colour Range RAL Colour Range. A colour match service is also available.

FLEXURAL STRENGTH

193 MPa

FACT: Flexural strength can be enhanced by the addition of woven reinforcement if required.

SIZE & THICKNESS

Panels can be manufactured to any length but with a width restriction of 1525mm. Standard product range can be manufactured to literally any thickness from 2mm upward.

TENSILE STRENGTH

123MPa

TENSILE MODULUS

7.1 GPa **GRP** sheet is up to seven times stronger than mild steel on a weight for weight basis.

THERMAL CONDUCTIVITY

FYBATEX: 0.2 W/m2K

LOGISTICS

Panels are usually supplied on pallets and can be delivered anywhere in the EU within approximately 10 -14 working days under normal circumstances. Each panel can be marked with a location code and panel size on the protective covering of the goods if required.